

Tips and Information for Use

Our mouth mirrors

SE plus

TOPvision FS Rhodium MEGA FS Rhodium

ULTRA FS + ULTRAvision FS

RELAX FS Rhodium + RELAX FS ULTRA

can be cleaned, sterilised and disinfected by all usual methods.

Please see also our manufacturer's information EN ISO 17664.

PRECAUTION

Do not use hard brushes or sponges:

Because these would scratch the mirror. Especially Front Surface mirrors should not be cleaned by abrasive rubbing or scrubbing.



Picture 1 - Scratches

Such scratches arise mainly on FS mouth mirrors that are coated on the front surface.

Take care that the decalcification in your thermo disinfectant (washer) functions properly:

By this way you avoid calciferous residues, which would blind the mirror.

Take care that the water inside the washer is not polluted by hard or suspended particles:

Hard particles (e.g. residues of cement) can damage the mirror surface.

Make sure that pointed instruments do not touch the mirror surface to avoid scratches

Do not sterilise with "Quick Sterilisation Programs":

Glass has another expansion coefficient as stainless steel. Therefore unusual rapid and high changes in temperature in the sterilisation device may lead to tensions in the glass and can also lead to glass cracks.

Ultrasonic is not suitable for Mouth Mirrors

(see AKI Brochure, no. 4, 2016 „Instrumentenaufbereitung in der Zahnarztpraxis richtig gemacht“)

Amongst others, the mirror surface can be impaired.

Use acid-containing refresh liquids only for ULTRA FS and Rhodium FS mirrors:

Such called refresh liquids like Neodisher N contain phosphoric-acids. Thus the silver coated mirrors might be destroyed.

E. HAHNENKRATT GmbH
Dentale Medizintechnik
Benzstraße 19
DE-75203 Königsbach-Stein

Fon 0049 (0)7232 /3029-0
Fax 0049 (0)7232 /3029-99
info@hahnenkratt.com
www.hahnenkratt.com

Geschäftsführender
Gesellschafter:
Peter Schepperheyne
Dipl. Wirt.-Ing. (FH)
Hendrik Schepperheyne
Dipl. Wirt.-Ing.
Amtsgericht Mannheim
HRB 501452
Steuer-Nr. 4117957752
DE 811 122 146

AVOIDING CALCIFEROUS DEPOSITIONS and CRUSTIFICATIONS

1. To avoid adherent contamination, put the instruments into disinfectant liquids **immediately** after use and clean them instantly.
2. Mouth mirrors should preferably be **rinsed with fully deionised water**.



Picture 2 -
Calciferous Residues

If tap water is used for rinsing, only absolutely dry instruments have to be placed in the steriliser in order to avoid **calciferous residues** and/or watermarks.

During sterilisation with high temperatures, these residues will even bake in the glass or in the ULTRA FS mirror coating and cannot be removed.

3. If the decalcification of the washer is not correctly adjusted, calciferous residues will impair the mirror quality.

FS RHODIUM: EASY REMOVING OF WATERMARKS, CALCIFEROUS RESIDUES and CRUSTIFICATIONS

This is **only** possible with mouth mirrors coated with **FS Rhodium** because they are coated with a **special HAHNENKRATT FS coating that provides an "anti-stick sealing" like Teflon**.

1. Remove calciferous residues with a soft brush and cleaning liquids.
2. Rhodium is a precious metal as gold and as a precious metal even resistant against acids. Therefore any calciferous residues can be removed by **simply cleaning with acid-containing refresh liquids, e.g. Neodisher N**.

Why is this **not** possible with other front or rear surface mirrors?

1. With SE plus mirrors, coated with silver on the rear surface of the glass, removing of the calciferous residues with liquids containing acids is **not** possible, because calciferous residues burns deeply into the glass surface due to the high temperatures during sterilisation.
2. **The ULTRA FS and ULTRAvision FS are coated with such called dielectric layers. Calciferous residues can bake in these layers and cannot be removed (see picture 2).**

YOUR BENEFITS at a glance

	ULTRA FS + ULTRAvision FS RELAX FS ULTRA	Rhodium FS: MEGA + TOPvision + RELAX	SE plus
Acid-Resistance	Yes	Yes	No
Easy removing of calciferous residues	No	Yes	No

Stand: 10/2019

E. HAHNENKRATT GmbH
Dentale Medizintechnik
Benzstraße 19
DE-75203 Königsbach-Stein

Fon 0049 (0)7232 /3029-0
Fax 0049 (0)7232 /3029-99
info@hahnenkratt.com
www.hahnenkratt.com

Geschäftsführender
Gesellschafter:
Peter Schepperheyne
Dipl. Wirt.-Ing. (FH)
Hendrik Schepperheyne
Dipl. Wirt.-Ing.
Amtsgericht Mannheim
HRB 501452
Steuer-Nr. 4117957752
DE 811 122 146